

UBE UBEPOL BR360L Non-Oil Extended Synthetic Rubber Vulcanizate (Cured 50 Minutes at 145°C)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Description: UBEPOL BR is UBE's line of polybutadiene rubber products. Information provided by UBE.

Order this product through the following link:

http://www.lookpolymers.com/polymer_UBE-UBEPOL-BR360L-Non-Oil-Extended-Synthetic-Rubber-Vulcanizate-Cured-50-Minutes-at-145C.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	64	64	ASTM D412
Tensile Strength at Break	19.1 MPa	2770 psi	ASTM D412
Elongation at Break	500 %	500 %	ASTM D412
100% Modulus	0.00230 GPa	0.334 ksi	ASTM D412
200% Modulus	0.00560 GPa	0.812 ksi	ASTM D412
300% Modulus	0.0106 GPa	1.54 ksi	ASTM D412
Rebound	61 %	61 %	BS.903,PART22
Tear Strength	53.0 kN/m	302 pli	ASTM D624
Abrasion	111	111	Lombourn Abrasion Index (Iwamoto Seisakusyo, Japan); UBE Method
	241	241	Pico Abrasion Index; ASTM D2228
Compression Set	13 %	13 %	Method B, 70°C, 72hrs; ASTM D395

Descriptive Properties	Value	Comments
Cut Generation De Mattia Flexing Machine	Min 300,000 times	ASTM D430
Cut Growth (2mm-->15mm) De Mattia Flexing Machine	1900 times	ASTM D313
Goodrich Flex, 0.175" Stroke, 55lb, 100°C, P.S.	5%	ASTM D623 (24°C change in temperature)
Wet Skid Resistance on Safety-Walk	17	UBE Method (British Portable Skid Resistance Tester)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China