

## UBE UBEPOL VCR406 Synthetic Rubber Vulcanizate (Cured 50 Minutes at 145°C)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Description: UBEPOL-VCR is a new type of synthetic rubber system developed by UBE's original technology. UBEPOL-VCR consists of micro-dispersed syndiotactic 1,2-polybutadiene (SPB) with high melting point and crystallinity, and high cis-1,4-polybutadiene rubber matrix. UBEPOL-VCR is improved on the processability and a lot of physical properties of the conventional polybutadiene rubber (BR).Information provided by UBE.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_UBE-UBEPOL-VCR406-Synthetic-Rubber-Vulcanizate-Cured-50-Minutes-at-145C.php](http://www.lookpolymers.com/polymer_UBE-UBEPOL-VCR406-Synthetic-Rubber-Vulcanizate-Cured-50-Minutes-at-145C.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	67	67	ASTM D412
Tensile Strength at Break	18.4 MPa	2670 psi	ASTM D412
Elongation at Break	460 %	460 %	ASTM D412
100% Modulus	0.00290 GPa	0.421 ksi	ASTM D412
200% Modulus	0.00740 GPa	1.07 ksi	ASTM D412
300% Modulus	0.0127 GPa	1.84 ksi	ASTM D412
Rebound	53 %	53 %	BS.903,PART22
Tear Strength	54.0 kN/m	308 pli	ASTM D624
Abrasion	100	100	Lombourn Abrasion Index (Iwamoto Seisakusyo, Japan); UBE Method
	268	268	Pico Abrasion Index; ASTM D2228
Compression Set	16 %	16 %	Method B, 70°C, 72hrs; ASTM D395

Descriptive Properties	Value	Comments
Cut Generation De Mattia Flexing Machine	Min 300,000 times	ASTM D430
Cut Growth (2mm-->15mm) De Mattia Flexing Machine	10000 times	ASTM D313
Goodrich Flex, 0.175" Stroke, 55lb, 100°C, P.S.	12%	ASTM D623 (35°C change in temperature)
Wet Skid Resistance on Safety-Walk	20	UBE Method (British Portable Skid Resistance Tester)

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China