

UBE UBESTA® 3020X25L Rigid Automotive Grade Nylon 12

Category : Polymer , Thermoplastic , Nylon , Nylon 12

Material Notes:

Description: UBE UBESTA® Automotive grade Nylon 12Comments: for coating steel and aluminumInformation provided by UBE.

Order this product through the following link:

http://www.lookpolymers.com/polymer_UBE-UBESTA-3020X25L-Rigid-Automotive-Grade-Nylon-12.php

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in³	ASTM D792
Melt Flow	18 g/10 min	18 g/10 min	ASTM D1238R
	@Load 2.16 kg, Temperature 235 °C	@Load 4.76 lb, Temperature 455 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	71	71	ASTM D2240
Tensile Strength at Break	>= 45.0 MPa	>= 6530 psi	ASTM D638
Tensile Strength, Yield	38.0 MPa	5510 psi	ASTM D638
Elongation at Break	>= 250 %	>= 250 %	ASTM D638
Flexural Strength	48.0 MPa	6960 psi	ASTM D790
Flexural Modulus	1.22 GPa	177 ksi	ASTM D790
Izod Impact, Notched	0.600 J/cm	1.12 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	178 °C	352 °F	ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	140 °C	284 °F	ASTM D648

Processing Properties	Metric	English	Comments
Processing Temperature	230 °C	446 °F	Flange Temperature for T-Die Cast Film Extrusion
Feed Temperature	40.0 °C	104 °F	Injection Molding
Zone 1	190 °C	374 °F	For T-Die Cast Film Extrusion
	230 °C	446 °F	For 8x1 mm Tube Extrusion
Zone 2	210 °C	410 °F	For T-Die Cast Film Extrusion

Processing Properties	Metric	English	Comments
Zone 3	220 °C	428 °F	For 8x1 mm Tube Extrusion
	230 °C	446 °F	For T-Die Cast Film Extrusion
Zone 4	215 °C	419 °F	For 8x1 mm Tube Extrusion
Die Temperature	230 °C	446 °F	For T-Die Cast Film Extrusion
Mold Temperature	40.0 - 60.0 °C	104 - 140 °F	Injection Molding
Injection Velocity	100 mm/sec	3.94 in/sec	Injection Molding
Die Opening	0.0400 cm	0.0157 in	For T-Die Cast Film Extrusion
Roll Temperature	50.0 °C	122 °F	Chill Roll Temperature for T-Die Cast Film Extrusion
Drying Temperature	80.0 °C	176 °F	Option 1
	100 °C	212 °F	Option 2
	110 °C	230 °F	Option 3
Dry Time	2 - 4 hour	2 - 4 hour	Option 3
	4 - 6 hour	4 - 6 hour	Option 2
	6 - 8 hour	6 - 8 hour	Option 1
Injection Pressure	40.0 - 50.0 MPa	5800 - 7250 psi	Injection Molding (Injection pressure should be increased when molding thin wall parts. Pressure up to 75 bar can be used here.)
Hold Pressure	25.0 - 50.0 MPa	3630 - 7250 psi	Injection Molding
Back Pressure	5.00 MPa	725 psi	Injection Molding
Screw Speed	15 - 76 rpm	15 - 76 rpm	For 8x1 mm Tube Extrusion

Descriptive Properties	Value	Comments
C/R	3-3.5:1	For 8x1 mm Tube Extrusion
Calibrating Vacuum	100 mbar	For 8x1 mm Tube Extrusion
Calibration	9.95 mm	For 8x1 mm Tube Extrusion
Compression Ratio	2.5-3.5:1	Injection Molding
	min 3:1	For 8x1 mm Tube Extrusion
Die Diameter	16 mm	For 8x1 mm Tube Extrusion

Descriptive Properties	Value	Comments
Extruder	Barmag, Screw Diameter = 30 mm	For T-Die Cast Film Extrusion
Extruder Characteristics	65 mm screw diameter	For 8x1 mm Tube Extrusion
Film Thickness	60 microns	For T-Die Cast Film Extrusion
Flight Depth in the Feeding Zone	10-15% of Screw Diameter	Injection Molding
Flight Depth in the Metering Zone	5-7% of Screw Diameter	Injection Molding
Haul Off Speed	5 m/min	For T-Die Cast Film Extrusion
Haul Speed	10-55 m/min	For 8x1 mm Tube Extrusion
L/D Ratio	25:1	For 8x1 mm Tube Extrusion
	min 20:1	Injection Molding
Length of Compression Zone	25-45% of total screw length	Injection Molding
	30% of screw length	For 8x1 mm Tube Extrusion
Length of Feeding Zone	20-40% of total screw length	Injection Molding
	30-40% of screw length	For 8x1 mm Tube Extrusion
Length of Metering Zone	30-45% of screw length	For 8x1 mm Tube Extrusion
	35-45% of total screw length	Injection Molding
Mandrel Diameter	12 mm	For 8x1 mm Tube Extrusion
Peripheral screw speed	10 m/min	Injection Molding
Water Temperature	10-18°C	For 8x1 mm Tube Extrusion

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China