

Unifrax Anchor-Loc®2 2200 Ceramic Fiber Modules

Category: Ceramic, Oxide, Silicon Oxide

Material Notes:

Anchor-Loc®2 ceramic fiber modules extend the successful performance of standard Anchor-Loc folded modules to a product form featuring laminated fiber blanket constructin. This product combines advancements in fiber chemistry, manufacturing technology, and attachment hardware design to provide an economical lining system for a wide range of heat processing vessels. The Fibermass® manufacturing technique used to fabricate Anchor-Loc2 modules bonds layers of refractory ceramic fiber blanket into a strong pliable fiber block. Spun ceramic fiber blankets which feature high tensile strength for improved resistance to mechanical abuse, vibration, and gas velocity are used in the construction of Anchor-Loc2 Fibermass blocks. A proprietary fiber treatment decreases fiber dusting and irritation while increasing block flexibility, making the module easy to compress into place. Modules are available in two temperature grades based on construction from Durablanket® HP-S or Durablanket 2600. In all Anchor-Loc2 modules, Fibermass blocks are secured to the metallic module anchor with a pair of stainless steel support tubes. Flanges on one end of the support tubes effectively lock the position of the tubes relative to the anchor at the time of installation. Product AdvantagesFaster temperature cyclingLower heat storageLower fuel costsIncreased productivityLower installed costEasier repairsResistance to thermal shockApplicationsStress relievign furnacesAnnealing furnacesCar bottom heat treating furnacesProcess heatersReheat furnacesFurnace, kiln and boiler liningsIncineration equipment and stack liningsSoaking pit coversLadle preheatersForge furnacesInformation Provided by Unifrax LLCC

Order this product through the following link:

http://www.lookpolymers.com/polymer_Unifrax-Anchor-Loc2-2200-Ceramic-Fiber-Modules.php

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	1149 °C	2100 °F	Recommended Operating Temperature

Component Elements Properties	Metric	English	Comments	
Al203	43 - 47 %	43 - 47 %		
SiO2	53 - 57 %	53 - 57 %		

Descriptive Properties	Value	Comments
Na203 (%)	<0.5	
Temperature Grade (°C)	1260	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China