Unifrax Fiberfrax® HS95C High Purity High-Index Fiber

Category : Ceramic , Oxide , Aluminum Oxide , Silicon Oxide

Material Notes:

In addition to Fiberfrax Bulk Fibers, Unifrax has the ability to produce many different specialty fibers that provide a variety of desirable performance properties for certain applications. These fibers can be classified into the following general categories:High-Index FibersHigh-Temperature FibersLarge-Diameter FibersMilled FibersFiber index is a measurement which determines the amount of fiberized material in the actual fiber. During fiber manufacturing, shot or unfiberized material is produced as a natural product of the fiberization process. Unifrax has the ability to reduce the amount of shot in a fiber by controlling the furnacing process or by washing out the unfiberized material. Fiberfrax High-Index have proven to be a good reinforcement material for use in automotive break lining and other friction material. These high-index fibers provide a variety of desirable properties such as:Frictional stabilityHigh-temperature frictional performanceFade resistanceFlexural reinforcementFiberfrax High-Index fibers can also be used as a mechanical thixotrope in coatings applications offering reinforcement and fire resistance as additional benefits. These fibers offer the following unique propertiesExcellent high-temperature stabilityGood strength and high modulusLow coefficient of thermal expansionSuperior chemical resistanceVery low moisture absorptionThe thixotropic properties of Fiberfrax High-Index Fibers in conjunction with the mechanical and physical properties they have to offer make them an excellent candidate for use in:MasticsAdhesivesThick Film CoatingsFire Protective MaterialsCaulks, Putties, and SealantsInformation Provided by Unifrax ILLC

Order this product through the following link:

http://www.lookpolymers.com/polymer_Unifrax-Fiberfrax-HS95C-High-Purity-High-Index-Fiber.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.73 g/cc	2.73 g/cc	
Thermal Properties	Metric	English	Comments
Melting Point	1760 °C	3200 °F	
Maximum Service Temperature, Air	1175 °C	2147 °F	Recommended Operating Temperature

Component Elements Properties	Metric	English	Comments
AI203	47 - 52 %	47 - 52 %	
NaO2	<= 0.50 %	<= 0.50 %	
SiO2	48 - 53 %	48 - 53 %	

Descriptive Properties	Value	Comments
Average Fiber Diameter (microns)	1-2.5	
Chopping	Medium	
Color	White	



Descriptive Properties	Value	Comments
Temperature Grade (°C)	1260	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China