

Unifrax Fiberfrax® LDS Moldable Moldable Insulation

Category : Ceramic

Material Notes:

Fiberfrax LDS and LDS-AL moldables consist of Fiberfrax ceramic fibers dispersed in a sticky water-based refractory binder. These materials have a putty-like consistency which permits application by caulking, troweling, or hand forming. Both products adhere well to most surfaces. Drying is accomplished at a noncritical, elevated temperature, and the resulting dried material is strong, hard, and erosion resistant. LDS-AL moldable possesses excellent resistance to wetting by many nonferrous molten metals and is used extensively in molten aluminum contact applications. Typical Applications Patch refractory joints and cracks Hardware protection of ceramic fiber furnace linings Patch around burner blocks Refractory backup Information Provided by Unifrax I LLC

Order this product through the following link:

http://www.lookpolymers.com/polymer_Unifrax-Fiberfrax-LDS-Moldable-Moldable-Insulation.php

Physical Properties	Metric	English	Comments
Density	0.801 g/cc	0.0289 lb/in ³	Dry
	1.36 g/cc	0.0492 lb/in ³	Wet
Solids Content	55 %	55 %	
Loss On Ignition	5.0 %	5.0 %	

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.00276 GPa	0.400 ksi	Dry

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	1093 °C	1999 °F	Recommended Operating Temperature
Shrinkage	4.0 %	4.0 %	
	@Temperature 1090 °C, Time 86400 sec	@Temperature 1990 °F, Time 24.0 hour	

Descriptive Properties	Value	Comments
Appearance	Sticky putty	
Molten Aluminum Wetting Resistance	Good	
Temperature Grade (°F)	2300	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China