

Unifrax Fiberfrax® Vari-Form™ A Casting Mix

Category: Ceramic, Potting/Casting Ceramic

Material Notes:

Fiberfrax FC-25 tamping mix and Vari-Form™ castable materials provide casting mixes which can be applied in small areas such as furnace access and site doors, tube sheets, and as a refractory backup. FC-25 tamping mix is a wet mix containing Fiberfrax fibers and inorganic binders. It is poured directly from the container and tamped into place. Dry density is 20-25 pounds/cubic foot. Vari-Form is a dry mix available in two density grades of 30-40 and 50-60 pounds/cubic foot. Water is added to the dry product at the job site and mixed thoroughly. It is then simply poured and troweled into the area to be insulated. The mix sets in about 18 hours and can then be heated to operating temperature. Typical Applications Backup insulationLadle backup insulationInduction furnace insulationFornace door insulationInformation Provided by Unifrax I LLC

Order this product through the following link:

http://www.lookpolymers.com/polymer_Unifrax-Fiberfrax-Vari-Form-A-Casting-Mix.php

| Physical Properties | Metric | English | Comments |
|---------------------|--------------------|------------------------------------|----------|
| Density | 0.481 - 0.641 g/cc | 0.0174 - 0.0231 lb/in ³ | Dry |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|----------------------------|---------------------|----------|
| Modulus of Rupture | 0.000138 - 0.000345 GPa | 0.0200 - 0.0500 ksi | Dry |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|--|---|--------------------------------------|
| Maximum Service Temperature, Air | 982 °C | 1800 °F | Recommended Operating Temperature |
| Shrinkage | 1.6 % | 1.6 % | |
| | @Temperature 982 °C, Time 86400 sec | @Temperature 1800 °F, Time 24.0 hour | |

| Descriptive Properties | Value | Comments |
|------------------------|-----------------|----------|
| Appearance | Dry gray fibers | |
| Temperature Grade (°F) | 2200 | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China