

## Unipetrol PE HD LITEN® RL 58 HDPE

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

**Material Notes:**

Made for injection molding and special applications Information provided by Unipetrol RPA

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Unipetrol-PE-HD-LITEN-RL-58-HDPE.php](http://www.lookpolymers.com/polymer_Unipetrol-PE-HD-LITEN-RL-58-HDPE.php)

Physical Properties	Metric	English	Comments
Density	0.950 g/cc	0.0343 lb/in <sup>3</sup>	ISO 1183
ESCR 100% Igepal®	20 hour @Temperature 50.0 °C	20 hour @Temperature 122 °F	ASTM D1693
Melt Flow	3.0 g/10 min @Load 2.16 kg, Temperature 190 °C	3.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	57	57	ISO 868
Tensile Strength, Yield	20.0 MPa	2900 psi	ISO 527
Elongation at Yield	10 %	10 %	ISO 527
Flexural Modulus	0.750 GPa	109 ksi	ISO 178
Charpy Impact, Notched	0.600 J/cm <sup>2</sup> @Temperature -30.0 °C	2.86 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 179
	1.30 J/cm <sup>2</sup> @Temperature 23.0 °C	6.19 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Vicat Softening Point	124 °C	255 °F	ISO 306

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China