

Unipetrol PE HD LITEN® SB/SL 20 HDPE

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

Material Notes:

Made for blow molding, tubular film and special applications. Information provided by Unipetrol RPA

Order this product through the following link:

http://www.lookpolymers.com/polymer_Unipetrol-PE-HD-LITEN-SBSL-20-HDPE.php

Physical Properties	Metric	English	Comments
Density	0.938 g/cc	0.0339 lb/in ³	ISO 1183
ESCR 100% Igepal®	>= 350 hour @Temperature 50.0 °C	>= 350 hour @Temperature 122 °F	ASTM D1693
Melt Flow	0.20 g/10 min @Load 2.16 kg, Temperature 190 °C	0.20 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133
	1.0 g/10 min @Load 2.16 kg, Temperature 190 °C	1.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133
	22 g/10 min @Load 2.16 kg, Temperature 190 °C	22 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	56	56	ISO 868
Tensile Strength, Yield	17.0 MPa	2470 psi	ISO 527
Elongation at Yield	10 %	10 %	ISO 527
Flexural Modulus	0.600 GPa	87.0 ksi	ISO 178
Charpy Impact, Notched	0.140 J/cm ² @Temperature 23.0 °C	0.666 ft-lb/in ² @Temperature 73.4 °F	ISO 179
	0.500 J/cm ² @Temperature -30.0 °C	2.38 ft-lb/in ² @Temperature -22.0 °F	ISO 179

Thermal Properties	Metric	English	Comments
Vicat Softening Point	114 °C	237 °F	ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China