

Unipetrol S Sorbent Chezacarb

Category: Carbon, Carbon Black

Material Notes:

Sorbent Chezacarb is made in two sorts: S and SH. Both sorts are produced by modification of high-conductive carbon black Chezacarb, sort B. Sorbent Chezacarb S is determined for petroleum crash liquidation, e.g. for removal of free hydrocarbons and their derivates from water or solid surface. Sorbent Chezacarb SH is determined for sorption and discolouring processes in aqueous solutions. Product is not classified as dangerous according to EC Directives.Information provided by Unipetrol RPA

Order this product through the following link:

http://www.lookpolymers.com/polymer_Unipetrol-S-Sorbent-Chezacarb.php

| Physical Properties | Metric | English | Comments |
|--------------------------|---------------|-------------------|----------------|
| Bulk Density | <= 0.160 g/cc | <= 0.00578 lb/in³ | |
| Oil Absorption | >= 4.0 % | >= 4.0 % | g/g of sorbent |
| pH | 6.5 - 9.0 | 6.5 - 9.0 | |
| Iodine Absorption Number | 950 - 1200 | 950 - 1200 | mg/g |
| Ash | <= 1.7 % | <= 1.7 % | |
| Evaporation Loss | <= 1.0 % | <= 1.0 % | |

| Component Elements Properties | Metric | English | Comments | |
|-------------------------------|-----------|-----------|----------|--|
| Iron, Fe | <= 0.18 % | <= 0.18 % | | |
| Nickel, Ni | <= 0.25 % | <= 0.25 % | | |
| Vanadium, V | <= 0.50 % | <= 0.50 % | | |

| Descriptive Properties | Value | Comments |
|--------------------------|---------|----------|
| DBP Absorption (ml/100g) | 370-450 | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China