

United Cast Bar Unibar 500-7 Continuously Cast Spheroidal Graphite Iron

Category : Metal , Ferrous Metal , Cast Iron , Gray Cast Iron

Material Notes:

Offers higher wear resistance, strength & heat-treatment response while still possessing good machinability and excellent surface finishes. Noise and vibration damping are good in this grade. Unibar 500-7 can be hardened by conventional methods. Information provided by United Cast Bar Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_United-Cast-Bar-Unibar-500-7-Continuously-Cast-Spheroidal-Graphite-Iron.php

Physical Properties	Metric	English	Comments
Density	7.30 g/cc	0.264 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Brinell	170 - 230	170 - 230	10 mm ball
	@Load 3000 kg	@Load 6610 lb	
Tensile Strength	420 MPa	60900 psi	
	@Diameter 105 - 200 mm	@Diameter 4.13 - 7.87 in	
	420 MPa	60900 psi	
	@Diameter 205 - 600 mm	@Diameter 8.07 - 23.6 in	
	450 MPa	65300 psi	
	@Diameter 55.0 - 100 mm	@Diameter 2.17 - 3.94 in	
	500 MPa	72500 psi	
	@Diameter 25.0 - 50.0 mm	@Diameter 0.984 - 1.97 in	
Tensile Stress	290 MPa	42100 psi	
	@Diameter 105 - 200 mm, Strain 0.200 %	@Diameter 4.13 - 7.87 in, Strain 0.200 %	
	290 MPa	42100 psi	
	@Diameter 205 - 600 mm, Strain 0.200 %	@Diameter 8.07 - 23.6 in, Strain 0.200 %	
	300 MPa	43500 psi	
	@Diameter 55.0 - 100 mm,	@Diameter 2.17 - 3.94 in,	

Mechanical Properties	Strain 0.200 % Metric	Strain 0.200 % English	Comments
	320 MPa	46400 psi	
	@Diameter 25.0 - 50.0 mm, Strain 0.200 %	@Diameter 0.984 - 1.97 in, Strain 0.200 %	
Elongation at Break	5.0 %	5.0 %	
	@Thickness 105 - 200 mm	@Thickness 4.13 - 7.87 in	
	5.0 %	5.0 %	
	@Thickness 205 - 600 mm	@Thickness 8.07 - 23.6 in	
	7.0 %	7.0 %	
	@Thickness 25.0 - 50.0 mm	@Thickness 0.984 - 1.97 in	
	7.0 %	7.0 %	
	@Thickness 55.0 - 100 mm	@Thickness 2.17 - 3.94 in	

Component Elements Properties	Metric	English	Comments
Carbon, C	3.25 - 3.7 %	3.25 - 3.7 %	
Iron, Fe	92.83 - 94.19 %	92.83 - 94.19 %	as balance
Magnesium, Mg	0.040 - 0.070 %	0.040 - 0.070 %	
Manganese, Mn	0.10 - 0.30 %	0.10 - 0.30 %	
Phosphorous, P	0.015 - 0.080 %	0.015 - 0.080 %	
Silicon, Si	2.4 - 3.0 %	2.4 - 3.0 %	
Sulfur, S	0.0050 - 0.020 %	0.0050 - 0.020 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China