

Unitika B2040G33 PA66, 33% Glass Fiber Reinforced, Dry

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

Information provided by Unitika Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Unitika-B2040G33-PA66-33-Glass-Fiber-Reinforced-Dry.php

Physical Properties	Metric	English	Comments
Density	1.39 g/cc	0.0502 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	1.7 %	1.7 %	50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Linear Mold Shrinkage, Transverse	0.0080 cm/cm	0.0080 in/in	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ISO 2039
Tensile Strength at Break	170 MPa	24700 psi	ISO 527-1/-2
Elongation at Break	3.0 %	3.0 %	ISO 527-1/-2
Tensile Modulus	10.0 GPa	1450 ksi	ISO 527-1/-2
Flexural Strength	260 MPa	37700 psi	ISO 178
Flexural Modulus	9.00 GPa	1310 ksi	ISO 178
Charpy Impact Unnotched	7.50 J/cm ²	35.7 ft-lb/in ²	ISO 179-1
Charpy Impact, Notched	1.00 J/cm ²	4.76 ft-lb/in ²	ISO 179-1

Thermal Properties	Metric	English	Comments
CTE, linear	40.0 μm/m-°C	22.2 μin/in-°F	ISO 11359-2
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	230 °C	446 °F	ISO 75-1/-2

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity Electrical Properties	1.00e+12 ohm-cm Metric	1.00e+12 ohm-cm English	IEC 60093 Comments
Dielectric Constant	3.5 @Frequency 1.00e+6 Hz	3.5 @Frequency 1.00e+6 Hz	IEC 60250
Dielectric Strength	35.0 kV/mm @Thickness 1.00 mm	889 kV/in @Thickness 0.0394 in	IEC 60243-1
Dissipation Factor	0.020 @Frequency 1.00e+6 Hz	0.020 @Frequency 1.00e+6 Hz	IEC 60250

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China