

## Universal Wire Works ER16-8-2 Stainless Steel Bare Wire

Category : Metal , Ferrous Metal , Stainless Steel

### Material Notes:

This alloy was designed for welding stainless steel for high pressure, high temperature piping systems. The weld deposit usually has a ferrite number no higher than 5. The deposit also has good hot ductility properties, which offer greater freedom from weld or crater cracking even under restraint conditions. The weld metal is usable in the as-welded or solution-treated condition. Information provided by Universal Wire Works for their line of welding wire and filler metal.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Universal-Wire-Works-ER16-8-2-Stainless-Steel-Bare-Wire.php](http://www.lookpolymers.com/polymer_Universal-Wire-Works-ER16-8-2-Stainless-Steel-Bare-Wire.php)

Component Elements Properties	Metric	English	Comments
Chromium, Cr	16 %	16 %	
Iron, Fe	74 %	74 %	As Remainder
Molybdenum, Mo	2.0 %	2.0 %	
Nickel, Ni	8.0 %	8.0 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China