

**Victrex® PEEK 600P Polyetheretherketone (discontinued \*\*)**

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Unreinforced

**Material Notes:**

Product Description: High performance thermoplastic material, unreinforced PolyEtherEtherKetone (PEEK), semi crystalline, coarse powder for extrusion compounding, low flow, FDA food contact compliant Information provided by Victrex

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Victrex-PEEK-600P-Polyetheretherketone-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Victrex-PEEK-600P-Polyetheretherketone-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.30 g/cc	0.0470 lb/in <sup>3</sup>	ISO 1183
Viscosity	450000 cP @Temperature 400 °C	450000 cP @Temperature 752 °F	Melt; ISO 11443

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	90.0 MPa	13100 psi	Result based on similar products; ISO 527
Elongation at Break	30 %	30 %	Result based on similar products; ISO 527
Tensile Modulus	3.70 GPa	537 ksi	Result based on similar products; ISO 527
Flexural Strength	150 MPa	21800 psi	Result based on similar products; ISO 178
Flexural Modulus	4.10 GPa	595 ksi	Result based on similar products; ISO 178
Izod Impact, Notched (ISO)	7.50 kJ/m <sup>2</sup>	3.57 ft-lb/in <sup>2</sup>	Result based on similar products; ISO 180/A
Izod Impact, Unnotched (ISO)	NB	NB	Result based on similar products; ISO 180/U

Thermal Properties	Metric	English	Comments
Melting Point	343 °C	649 °F	ISO 11357
Glass Transition Temp, Tg	143 °C	289 °F	Onset; ISO 11357

Descriptive Properties	Value	Comments
Color	Natural	

**Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**