

Victrex® PEEK 90GL30 BLACK EU 30% Glass Fiber Filled, PolyEtherEtherKetone

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Glass Fiber Filled

Material Notes:

High performance thermoplastic material, 30% glass fiber reinforced PolyEtherEtherKetone (PEEK), semi crystalline, granules for injection molding, very easy flow, FDA and EU food contact compliant, color black. Typical Application Areas: Complex geometries with thinner cross sections or longer flow lengths where higher strength in a static system is required. Low coefficient of thermal expansion. Chemically resistant to aggressive environments, suitable for sterilization for medical and food contact applications. Information Provided by VICTREX®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Victrex-PEEK-90GL30-BLACK-EU-30-Glass-Fiber-Filled-PolyEtherEtherKetone.php

Physical Properties	Metric	English	Comments
Density	1.52 g/cc	0.0549 lb/in ³	Crystalline; ISO 1183
Water Absorption at Saturation	0.30 %	0.30 %	immersion; ISO 62-1
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	0.45 %	0.45 %	immersion; ISO 62-1
	@Temperature 100 °C	@Temperature 212 °F	
Viscosity	200000 cP	200000 cP	melt; ISO 11443
	@Temperature 400 °C	@Temperature 752 °F	
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	370°C nozzle, 180°C tool; ISO 294-4
Linear Mold Shrinkage, Transverse	0.0090 cm/cm	0.0090 in/in	370°C nozzle, 180°C tool; ISO 294-4
Spiral Flow	18.5 cm	7.28 in	370°C nozzle, 180°C tool
	@Thickness 1.00 mm	@Thickness 0.0394 in	
	22.0 cm	8.66 in	400°C nozzle, 200°C tool
	@Thickness 1.00 mm	@Thickness 0.0394 in	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	87	87	ISO 868
Tensile Strength at Break	40.0 MPa	5800 psi	ISO 527
	@Temperature 275 °C	@Temperature 527 °F	
	60.0 MPa	8700 psi	ISO 527
	@Temperature 225 °C	@Temperature 437 °F	
	70.0 MPa	10200 psi	

Mechanical Properties	Metric @ Temperature 175 °C	English @ Temperature 347 °F	ISO 527 Comments
	120 MPa	17400 psi	ISO 527
	@Temperature 125 °C	@Temperature 257 °F	
	180 MPa	26100 psi	ISO 527
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Elongation at Break	2.2 %	2.2 %	ISO 527
Tensile Modulus	12.0 GPa	1740 ksi	ISO 527
Flexural Strength	75.0 MPa	10900 psi	ISO 178
	@Temperature 275 °C	@Temperature 527 °F	
	115 MPa	16700 psi	ISO 178
	@Temperature 175 °C	@Temperature 347 °F	
	230 MPa	33400 psi	ISO 178
	@Temperature 125 °C	@Temperature 257 °F	
	275 MPa	39900 psi	ISO 178
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Flexural Modulus	11.5 GPa	1670 ksi	ISO 178
Compressive Strength	55.0 MPa	7980 psi	ISO 604
	@Temperature 200 °C	@Temperature 392 °F	
	160 MPa	23200 psi	ISO 604
	@Temperature 120 °C	@Temperature 248 °F	
	250 MPa	36300 psi	ISO 604
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Izod Impact, Notched (ISO)	8.00 kJ/m ²	3.81 ft-lb/in ²	ISO 180/A
Izod Impact, Unnotched (ISO)	40.0 kJ/m ²	19.0 ft-lb/in ²	ISO 180/U

Thermal Properties	Metric	English	Comments
CTE, linear	45.0 µm/m-°C	25.0 µin/in-°F	Average below Tg; ASTM D696
	@Temperature <=143 °C	@Temperature <=289 °F	
	110 µm/m-°C	61.1 µin/in-°F	Average above Tg; ASTM D696
	@Temperature >=143 °C	@Temperature >=289 °F	

Thermal Properties	Metric 20.0 µm/m-°C	English 11.1 µin/in-°F	Comments
CTE, linear, Parallel to Flow	@Temperature <= 143 °C	@Temperature <= 289 °F	Below Tg; ASTM D696
	20.0 µm/m-°C	11.1 µin/in-°F	
	@Temperature >= 143 °C	@Temperature >= 289 °F	Above Tg; ASTM D696
Thermal Conductivity	0.300 W/m-K	2.08 BTU-in/hr-ft²-°F	Average; ISO 22007-4
	0.350 W/m-K	2.43 BTU-in/hr-ft²-°F	Along flow; ISO 22007-4
Melting Point	343 °C	649 °F	ISO 11357
Deflection Temperature at 1.8 MPa (264 psi)	335 °C	635 °F	ISO 75A-f
Glass Transition Temp, Tg	143 °C	289 °F	ISO 11357
Glow Wire Test	960 °C	1760 °F	Fire Smoke Toxicity; IEC 60695-2-12
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Dielectric Strength	21.5 kV/mm	546 kV/in	IEC 60243-1
	@Thickness 2.00 mm	@Thickness 0.0787 in	
Comparative Tracking Index	150 V	150 V	IEC 60112

Processing Properties	Metric	English	Comments
Processing Temperature	<= 100 °C	<= 212 °F	Hopper Temperature
Nozzle Temperature	370 °C	698 °F	
Mold Temperature	170 - 200 °C	338 - 392 °F	
Dry Time	3.00 hour	3.00 hour	
	@Temperature 150 °C	@Temperature 302 °F	
	5.00 hour	5.00 hour	
	@Temperature 120 °C	@Temperature 248 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China