

Victrex® Vicote® 706 Polyetheretherketone (PEEK) Powder

Category: Polymer, Thermoplastic, Polyketone, Polyetheretherketone (PEEK)

Material Notes:

Properties: VICOTE 701-707 grades are specially developed powder coatings. They are available in various average particle sizes from 10 - 50 microns. The powders are off-white in color and are available in various melt viscosities depending on the film thickness and level of melt flow required. Typical film thicknesses range from < 100 microns up to 500 microns. Film thicknesses above 1 mm are possible by building up the coating thickness by the hot flocking technique. Like other non-coating grades of VICTREXPEEK polymer, VICOTE Coatings are thermoplastic in nature and exhibit flow above the melt temperature. When processed using the correct guidelines, the coatings will exhibit the excellent properties that VICTREX PEEK polymer is renowned for. High continuous use temperature of 260°C Excellent wear, abrasion and cut through resistance at these high temperatures Excellent chemical and radiation resistance Low level of extractables Hydrolysis resistant Inherently flame retardantAll information provided by Victrex.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Victrex-Vicote-706-Polyetheretherketone-PEEK-Powder.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|---------------|----------|
| Density | 1.32 g/cc | 0.0477 lb/in³ | ISO 1183 |

| Thermal Properties | Metric | English | Comments | |
|---------------------------|--------|---------|----------|--|
| Melting Point | 343 °C | 649 °F | DSC | |
| Glass Transition Temp, Tg | 143 °C | 289 °F | DSC | |
| UL RTI, Electrical | 260 °C | 500 °F | UL746B | |

| Processing Properties | Metric | English | Comments |
|-----------------------|-----------------|-----------------|----------------------|
| Drying Temperature | 120 °C | 248 °F | overnight before use |
| | 150 °C | 302 °F | |
| | @Time 10800 sec | @Time 3.00 hour | |

| Descriptive Properties | Value | Comments |
|------------------------|-------------|----------------|
| Konig Hardness | 200 seconds | BS EN ISO 1522 |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058



Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China