

## Victrex® Vicote® F808 Polyetheretherketone (PEEK) Liquid Dispersion

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK)

### Material Notes:

The VICOTE F808 natural, F809 natural and F810Blk grades have been specifically formulated to provide a resilient coating with high wear and abrasion resistance combined with excellent release properties on ferrous substrates such as carbon and cast steels. These properties are retained at high temperatures where other release coatings would potentially fail. VICOTE dispersions have a low level of extractables. All information provided by Victrex.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Victrex-Vicote-F808-Polyetheretherketone-PEEK-Liquid-Dispersion.php](http://www.lookpolymers.com/polymer_Victrex-Vicote-F808-Polyetheretherketone-PEEK-Liquid-Dispersion.php)

Physical Properties	Metric	English	Comments
Storage Temperature	5.00 - 25.0 °C	41.0 - 77.0 °F	

Mechanical Properties	Metric	English	Comments
Impact	1.0	1.0	1m, 1kg, Indent 5mm; ISO 6272
Coefficient of Friction	0.104	0.104	µm @ 10 min., Using 250N Load; ASTM G 133

Processing Properties	Metric	English	Comments
Drying Temperature	120 °C	248 °F	overnight before use
	150 °C	302 °F	
	@Time 10800 sec	@Time 3.00 hour	

Descriptive Properties	Value	Comments
Konig Hardness (seconds)	170	ISO 1522

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China