

## Vista Metals Duramold-5™ Cast Aluminum Mold Plate

Category : Metal , Nonferrous Metal , Aluminum Alloy , Aluminum Casting Alloy

**Material Notes:**

Used for molds for the automotive industry, blow molds, structural foam molds, rubber molds, low pressure injection molds, Thermoforming molds, R.I.M. and R.T.M. molding. Features: Excellent Machinability; Dimensional Stability; Excellent Weldability; High Strength to Weight Ratio; Enhanced Corrosion Resistance; Ultrasonically Inspected; Gauge 2" - 38"; widths up to 94". Surface Condition & Roughness: Machined 2 Sides (25 RMS) Sawed Surface (+.125"/-0)

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Vista-Metals-Duramold-5-Cast-Aluminum-Mold-Plate.php](http://www.lookpolymers.com/polymer_Vista-Metals-Duramold-5-Cast-Aluminum-Mold-Plate.php)

Physical Properties	Metric	English	Comments
Density	2.66 g/cc	0.0960 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Hardness, Brinell	70	70	
Tensile Strength, Ultimate	283 MPa	41000 psi	
Tensile Strength, Yield	124 MPa	18000 psi	
Elongation at Break	12 - 15 %	12 - 15 %	in 2"
Modulus of Elasticity	69.6 GPa	10100 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	23.6 $\mu\text{m}/\text{m}\cdot\text{°C}$	13.1 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 20.0 - 100 °C	@Temperature 68.0 - 212 °F	
Thermal Conductivity	24.1 $\mu\text{m}/\text{m}\cdot\text{°C}$	13.4 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 101 - 200 °C	@Temperature 213 - 392 °F	
	140 W/m-K	972 BTU-in/hr-ft <sup>2</sup> -°F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000059 ohm-cm	0.0000059 ohm-cm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**