

Voloknohim PA 6-210/310 Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

For production of plastics and industrial goods used in machine building and motor industry. Nylon 6 bright, not dyed and (or) heat stabilized
Information provided by Voloknokhim

Order this product through the following link:

http://www.lookpolymers.com/polymer_Voloknohim-PA-6-210310-Nylon-6.php

Physical Properties	Metric	English	Comments
Particle Size	1500 - 4000 µm	1500 - 4000 µm	chip length
Viscosity Measurement	<= 2.5	<= 2.5	Relative Viscosity
Collected Volatile Condensable Material	<= 1.5 %	<= 1.5 %	

Mechanical Properties	Metric	English	Comments
Charpy Impact, Notched	>= 0.500 J/cm ²	>= 2.38 ft-lb/in ²	

Processing Properties	Metric	English	Comments
Melt Temperature	>= 215 °C	>= 419 °F	
Moisture Content	<= 0.20 %	<= 0.20 %	

Descriptive Properties	Value	Comments
Fraction of not cut through chips by mass	0.5	up to 20 mm, % max
Quality of foreign and oxidized particles	18	100 g of product, max pieces

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China