

Von Roll Isola IMI E-Solder® 3025 Electrically Conductive Adhesive

Category : Polymer , Adhesive , Thermoset , Epoxy

Material Notes:

Data provided by Von Roll Isola USA.E-SOLDER® epoxy based resin systems can be used at room temperature on heat sensitive materials, can bond dissimilar materials, and do not have flux or residue to contaminate sensitive electronic components.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Von-Roll-Isola-IMI-E-Solder-3025-Electrically-Conductive-Adhesive.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	17.0 MPa	2470 psi	butt tensile strength per ASTM D426 on brass
Adhesive Bond Strength	14.0 MPa	2030 psi	Tensile shear per ASTM D1002 on etched Al panel

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 °C	302 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0400 ohm-cm	0.0400 ohm-cm	cured 24 hr at 25°C (77°F). Value is 0.004 Ohm-cm cured 3 hr at 65°C (150°F)

Processing Properties	Metric	English	Comments
Processing Temperature	65.0 °C	149 °F	Suggested baking time at this temperature is 4 hr.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China