

Von Roll Isola IMI E-Solder® 3026 Electrically Conductive Adhesive

Category : Polymer , Adhesive , Thermoset , Epoxy

Material Notes:

Data provided by Von Roll Isola USA.E-SOLDER® epoxy based resin systems can be used at room temperature on heat sensitive materials, can bond dissimilar materials, and do not have flux or residue to contaminate sensitive electronic components.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Von-Roll-Isola-IMI-E-Solder-3026-Electrically-Conductive-Adhesive.php

Mechanical Properties	Metric	English	Comments
Adhesive Bond Strength	9.70 MPa	1410 psi	Tensile shear per ASTM D1002 on etched Al panel

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	85.0 °C	185 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0100 ohm-cm	0.0100 ohm-cm	

Processing Properties	Metric	English	Comments
Processing Temperature	80.0 °C	176 °F	Suggested baking time at this temperature is 1.5 hr. May also be cured for shorter time at higher temperatures.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China