

Von Roll Isola IMI Varnish 704 Solventless Polyester Varnish for Electrical Insulation

Category: Polymer, Thermoset, Polyester, TS, Thermoset Polyester Solventless Electrical Varnish

Material Notes:

Data provided by Von Roll Isola USA.IMI solventless resins provide relatively void-free insulation for greater protection against severe environments and corona breakdown. Flash Point: 42°C. Usage Notes: Quick treatment of motor stators, using the pour-through method of application. Potting compound or brush-on resin between mica tape layers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Von-Roll-Isola-IMI-Varnish-704-Solventless-Polyester-Varnish-for-Electrical-Insulation.php

Physical Properties	Metric	English	Comments
Density	1.08 g/cc	0.0390 lb/in³	
Viscosity	1500 cP	1500 cP	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 °C	356 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	75.0 kV/mm	1910 kV/in	

Processing Properties	Metric	English	Comments
Processing Temperature	100 °C	212 °F	Suggested baking time at this temperature is 0.25 hr.

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China