

Von Roll Isola IMI Varnish 716 Solventless Polyester Varnish for Electrical Insulation

Category : Polymer , Thermoset , Polyester, TS , Thermoset Polyester Solventless Electrical Varnish

Material Notes:

Data provided by Von Roll Isola USA. IMI solventless resins provide relatively void-free insulation for greater protection against severe environments and corona breakdown. Flash Point: 56°C. Usage Notes: Treatment of motors and transformers. Excellent stability for dip tank and VPI application.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Von-Roll-Isola-IMI-Varnish-716-Solventless-Polyester-Varnish-for-Electrical-Insulation.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	
Viscosity	900 cP	900 cP	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 °C	356 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	161 kV/mm	4090 kV/in	

Processing Properties	Metric	English	Comments
Processing Temperature	160 °C	320 °F	Suggested baking time at this temperature is 1.5 hr.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China