

Von Roll Isola IMI Varnish 73522 Solventless Polyester Varnish for Electrical Insulation

Category : Polymer , Thermoset , Polyester, TS , Thermoset Polyester Solventless Electrical Varnish

Material Notes:

Data provided by Von Roll Isola USA. IMI solventless resins provide relatively void-free insulation for greater protection against severe environments and corona breakdown. Flash Point: 30°C. Usage Notes: Thixotropic version of IMI 73517

Order this product through the following link:

http://www.lookpolymers.com/polymer_Von-Roll-Isola-IMI-Varnish-73522-Solventless-Polyester-Varnish-for-Electrical-Insulation.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|---------------------------|----------|
| Density | 1.08 g/cc | 0.0390 lb/in ³ | |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|--------|---------|----------|
| Maximum Service Temperature, Air | 200 °C | 392 °F | |

| Electrical Properties | Metric | English | Comments |
|-----------------------|------------|-----------|----------|
| Dielectric Strength | 16.0 kV/mm | 406 kV/in | |

| Processing Properties | Metric | English | Comments |
|------------------------|--------|---------|--|
| Processing Temperature | 140 °C | 284 °F | Suggested baking time at this temperature is 0.5-2 hr. |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China