

## Von Roll Isola IMI Varnish 74011 Solventless Epoxy Varnish for Electrical Insulation

Category: Polymer, Thermoset, Epoxy, Solventless Epoxy Varnish, Electrical Insulation

## **Material Notes:**

Data provided by Von Roll Isola USA.IMI solventless resins provide relatively void-free insulation for greater protection against severe environments and corona breakdown. Flash Point: >93°C. Usage Notes: Treatment of stators, rotors, fields, armatures, and field coils where excellent oil, moisture, and chemical resistance is required.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Von-Roll-Isola-IMI-Varnish-74011-Solventless-Epoxy-Varnish-for-Electrical-Insulation.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in <sup>3</sup>	
Viscosity	1500 cP	1500 cP	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	155 °C	311 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	85.0 kV/mm	2160 kV/in	

Processing Properties	Metric	English	Comments
Processing Temperature	150 °C	302 °F	Suggested baking time at this temperature is 4-6 hr.

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China