

Von Roll Isola IMI Varnish 9637 Polyester Varnish for Electrical Insulation

Category : Polymer , Thermoset , Polyester, TS , Thermoset Polyester Solventless Electrical Varnish

Material Notes:

Data provided by Von Roll Isola USA. Flash Point: 29°C. Average solids: 48%. Usage Notes: Treating transformers, magnet coils, stators, fields, armatures, railway field coils, and bare copper coils.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Von-Roll-Isola-IMI-Varnish-9637-Polyester-Varnish-for-Electrical-Insulation.php

Physical Properties	Metric	English	Comments
Density	0.970 g/cc	0.0350 lb/in ³	
Viscosity	250 cP	250 cP	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 °C	356 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	122 kV/mm	3100 kV/in	

Processing Properties	Metric	English	Comments
Processing Temperature	150 °C	302 °F	Suggested baking time at this temperature is 1-4 hr.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China