

## Von Roll Isola IMI Varnish 9637AP Polyester Varnish for Electrical Insulation

Category : Polymer , Thermoset , Polyester, TS , Thermoset Polyester Solventless Electrical Varnish

**Material Notes:**

Data provided by Von Roll Isola USA. Flash Point: 53°C. Average solids: 48%. Usage Notes: Higher flash point version of IMI 9637

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Von-Roll-Isola-IMI-Varnish-9637AP-Polyester-Varnish-for-Electrical-Insulation.php](http://www.lookpolymers.com/polymer_Von-Roll-Isola-IMI-Varnish-9637AP-Polyester-Varnish-for-Electrical-Insulation.php)

Physical Properties	Metric	English	Comments
Density	0.970 g/cc	0.0350 lb/in <sup>3</sup>	
Viscosity	240 cP	240 cP	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 °C	356 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	122 kV/mm	3100 kV/in	

Processing Properties	Metric	English	Comments
Processing Temperature	150 °C	302 °F	Suggested baking time at this temperature is 1-6 hr.

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China