

Washington Penn Homopolymer Polypropylene 10% Talc Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Talc Filler

Material Notes:

Talc-filled polypropylene compounds have been tailored specifically to meet the requirements of each of the major automobile producers. Grades are available to meet FDA food and drug packaging requirements. These products have excellent mold detail and surface reproduction with fast set-up times. They are also available in an array of colors. Information provided by Washington Penn Plastic Co.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Washington-Penn-Homopolymer-Polypropylene-10-Talc-Filled.php

Physical Properties	Metric	English	Comments
Density	0.970 g/cc	0.0350 lb/in ³	ASTM D792
Filler Content	10 %	10 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	34.8 MPa	5050 psi	ASTM D638
Elongation at Break	35 %	35 %	ASTM D638
Elongation at Yield	11 %	11 %	ASTM D638
Flexural Modulus	1.90 GPa	275 ksi	1% Secant; ASTM D790
	2.07 GPa	300 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.320 J/cm	0.600 ft-lb/in	ASTM D256
Gardner Impact	0.904 J @Temperature 23.0 °C	0.667 ft-lb @Temperature 73.4 °F	ASTM D5420

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	107 °C	225 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China