

## Washington Penn Homopolymer Polypropylene 20% Talc Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Talc Filler

### Material Notes:

Talc-filled polypropylene compounds have been tailored specifically to meet the requirements of each of the major automobile producers. Grades are available to meet FDA food and drug packaging requirements. These products have excellent mold detail and surface reproduction with fast set-up times. They are also available in an array of colors. Information provided by Washington Penn Plastic Co.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Washington-Penn-Homopolymer-Polypropylene-20-Talc-Filled.php](http://www.lookpolymers.com/polymer_Washington-Penn-Homopolymer-Polypropylene-20-Talc-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in <sup>3</sup>	ASTM D792
Filler Content	20 %	20 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	34.8 MPa	5050 psi	ASTM D638
Elongation at Break	20 %	20 %	ASTM D638
Elongation at Yield	8.0 %	8.0 %	ASTM D638
Flexural Modulus	2.41 GPa	350 ksi	1% Secant; ASTM D790
	2.76 GPa	400 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.320 J/cm	0.600 ft-lb/in	ASTM D256
Gardner Impact	0.904 J @Temperature 23.0 °C	0.667 ft-lb @Temperature 73.4 °F	ASTM D5420

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	118 °C	245 °F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China