

Washington Penn Homopolymer Polypropylene 50% Calcium Carbonate Filled

Category: Polymer, Thermoplastic, Polypropylene (PP), Polypropylene with 50% Calcium Carbonate

Material Notes:

Calcium carbonate-filled polypropylene compounds have been tailored specifically to meet the requirements of each of the major automobile producers. Grades are available to meet FDA food and drug packaging requirements. These products have excellent mold detail and surface reproduction with fast set-up times. They are also available in an array of colors. Information provided by Washington Penn Plastic Co.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Washington-Penn-Homopolymer-Polypropylene-50-Calcium-Carbonate-Filled.php

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in³	ASTM D792
Filler Content	50 %	50 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	20.7 MPa	3000 psi	ASTM D638
Elongation at Break	50 %	50 %	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Flexural Modulus	2.59 GPa	375 ksi	1% Secant; ASTM D790
	2.96 GPa	430 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.374 J/cm	0.700 ft-lb/in	ASTM D256
Gardner Impact	17.2 J	12.7 ft-lb	ASTM D5420
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	107 °C	225 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China