

Washington Penn Medium Impact Copolymer 30% Talc Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Talc Filler

Material Notes:

Talc-filled polypropylene compounds have been tailored specifically to meet the requirements of each of the major automobile producers. Grades are available to meet FDA food and drug packaging requirements. These products have excellent mold detail and surface reproduction with fast set-up times. They are also available in an array of colors. Information provided by Washington Penn Plastic Co.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Washington-Penn-Medium-Impact-Copolymer-30-Talc-Filled.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ASTM D792
Filler Content	30 %	30 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	23.4 MPa	3400 psi	ASTM D638
Elongation at Break	40 %	40 %	ASTM D638
Elongation at Yield	7.0 %	7.0 %	ASTM D638
Flexural Modulus	2.14 GPa	310 ksi	1% Secant; ASTM D790
	2.65 GPa	385 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	ASTM D256
Gardner Impact	5.54 J	4.08 ft-lb	ASTM D5420
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	13.8 J	10.2 ft-lb	ASTM D5420
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	121 °C	250 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China