

Wellman EcoLon® MRGF1878-BK1 Nylon 6, 30% Mineral/Glass Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Glass/Mineral Reinforced

Material Notes:

All information provided by Wellman Engineered Resins.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-EcoLon-MRGF1878-BK1-Nylon-6-30-MineralGlass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.39 g/cc	0.0502 lb/in ³	ISO 1183-87
Linear Mold Shrinkage, Flow	0.0030 - 0.0070 cm/cm	0.0030 - 0.0070 in/in	DIS 294-4
Linear Mold Shrinkage, Transverse	0.0070 - 0.011 cm/cm	0.0070 - 0.011 in/in	DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	105 MPa	15200 psi	ISO 527-93
Elongation at Break	2.0 %	2.0 %	ISO 527-93
Flexural Strength	150 MPa	21800 psi	ISO 178-93
Flexural Modulus	7.10 GPa	1030 ksi	ISO 178-93
Izod Impact, Notched (ISO)	4.50 kJ/m ²	2.14 ft-lb/in ²	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	195 °C	383 °F	ISO 75-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China