

Wellman Wellamid® 42LN2-N Nylon 6, General Purpose

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

All information provided by Wellman Engineered Resins.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellamid-42LN2-N-Nylon-6-General-Purpose.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ISO 1183-87
Linear Mold Shrinkage, Flow	0.011 - 0.015 cm/cm	0.011 - 0.015 in/in	DIS 294-4
Linear Mold Shrinkage, Transverse	0.012 - 0.016 cm/cm	0.012 - 0.016 in/in	DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	85.0 MPa	12300 psi	ISO 527-93
Elongation at Break	35 %	35 %	ISO 527-93
Flexural Strength	100 MPa	14500 psi	ISO 178-93
Flexural Modulus	2.70 GPa	392 ksi	ISO 178-93
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	55.0 °C	131 °F	ISO 75-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China