

## Wellman Wellamid® FR22F-NBK3 Flame Retardant Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Unreinforced, Flame Retardant

**Material Notes:**

Description: Flame Retardant Nylon 66 Information provided by Wellman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Wellman-Wellamid-FR22F-NBK3-Flame-Retardant-Nylon-66.php](http://www.lookpolymers.com/polymer_Wellman-Wellamid-FR22F-NBK3-Flame-Retardant-Nylon-66.php)

Physical Properties	Metric	English	Comments
Density	1.32 g/cc	0.0477 lb/in <sup>3</sup>	ISO 1183-87
Linear Mold Shrinkage	0.014 - 0.018 cm/cm	0.014 - 0.018 in/in	ISO DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	55.0 MPa	7980 psi	ISO 527-93
Elongation at Break	8.0 %	8.0 %	ISO 527-93
Flexural Strength	90.0 MPa	13100 psi	ISO 178-93
Flexural Modulus	3.20 GPa	464 ksi	ISO 178-93
Izod Impact, Notched (ISO)	3.00 kJ/m <sup>2</sup>	1.43 ft-lb/in <sup>2</sup>	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	100 °C	212 °F	ISO 75-93
Flammability, UL94	V-0 @Thickness 0.790 mm	V-0 @Thickness 0.0311 in	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China