

## Wellman Wellamid® GF20-60 XE-BKDX9 Nylon 6, 20% Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 20% Glass Fiber Filled

**Material Notes:**

Chrysler DX9 color matched All information provided by Wellman Engineered Resins.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Wellman-Wellamid-GF20-60-XE-BKDX9-Nylon-6-20-Glass-Fiber-Reinforced.php](http://www.lookpolymers.com/polymer_Wellman-Wellamid-GF20-60-XE-BKDX9-Nylon-6-20-Glass-Fiber-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.28 g/cc	0.0462 lb/in <sup>3</sup>	ISO 1183-87
Linear Mold Shrinkage, Flow	0.0030 - 0.0070 cm/cm	0.0030 - 0.0070 in/in	DIS 294-4
Linear Mold Shrinkage, Transverse	0.0070 - 0.011 cm/cm	0.0070 - 0.011 in/in	DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	145 MPa	21000 psi	ISO 527-93
Elongation at Break	3.0 %	3.0 %	ISO 527-93
Flexural Strength	205 MPa	29700 psi	ISO 178-93
Flexural Modulus	6.30 GPa	914 ksi	ISO 178-93
Izod Impact, Notched (ISO)	6.00 kJ/m <sup>2</sup>	2.86 ft-lb/in <sup>2</sup>	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	205 °C	401 °F	ISO 75-93

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China