

Wellman Wellamid® GF30-60 XE-WBK Nylon 6, 30% Glass Reinforced, Weatherable

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

Material Notes:

All information provided by Wellman Engineered Resins.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellamid-GF30-60-XE-WBK-Nylon-6-30-Glass-Reinforced-Weatherable.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	ISO 1183-87
Linear Mold Shrinkage, Flow	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	DIS 294-4
Linear Mold Shrinkage, Transverse	0.0080 - 0.012 cm/cm	0.0080 - 0.012 in/in	DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	155 MPa	22500 psi	ISO 527-93
Elongation at Break	3.0 %	3.0 %	ISO 527-93
Flexural Strength	230 MPa	33400 psi	ISO 178-93
Flexural Modulus	8.70 GPa	1260 ksi	ISO 178-93
Izod Impact, Notched (ISO)	11.0 kJ/m ²	5.23 ft-lb/in ²	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	205 °C	401 °F	ISO 75-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China