

## Wellman Wellamid® GF33-66/6 XE-WBK 33% Glass Fiber Reinforced, Weatherable Black Nylon 66/6

Category : Polymer , Thermoplastic , Nylon , Nylon 6/66 , Nylon 66/6 , 30% Glass Fiber Reinforced

### Material Notes:

Description: Glass Fiber Reinforced, Weatherable Black Nylon 66/6 Information provided by Wellman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Wellman-Wellamid-GF33-666-XE-WBK-33-Glass-Fiber-Reinforced-Weatherable-Black-Nylon-666.php](http://www.lookpolymers.com/polymer_Wellman-Wellamid-GF33-666-XE-WBK-33-Glass-Fiber-Reinforced-Weatherable-Black-Nylon-666.php)

Physical Properties	Metric	English	Comments
Density	1.39 g/cc	0.0502 lb/in <sup>3</sup>	ISO 1183-87
Filler Content	33 %	33 %	
Linear Mold Shrinkage, Flow	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	ISO DIS 294-4
Linear Mold Shrinkage, Transverse	0.0070 - 0.011 cm/cm	0.0070 - 0.011 in/in	ISO DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	155 MPa	22500 psi	ISO 527-93
Elongation at Break	3.0 %	3.0 %	ISO 527-93
Flexural Strength	240 MPa	34800 psi	ISO 178-93
Flexural Modulus	8.60 GPa	1250 ksi	ISO 178-93
Izod Impact, Notched (ISO)	10.0 kJ/m <sup>2</sup>	4.76 ft-lb/in <sup>2</sup>	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	220 °C	428 °F	ISO 75-93

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China