

Wellman Wellamid® GFT13-66 XE-NBK1 13% Glass Fiber Reinforced, Impact Modified Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 10% Glass Fiber Filled

Material Notes:

Description: Glass Fiber Reinforced, Impact Modified Nylon 66 Information provided by Wellman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellamid-GFT13-66-XE-NBK1-13-Glass-Fiber-Reinforced-Impact-Modified-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ISO 1183-87
Filler Content	13 %	13 %	
Linear Mold Shrinkage, Flow	0.010 - 0.014 cm/cm	0.010 - 0.014 in/in	ISO DIS 294-4
Linear Mold Shrinkage, Transverse	0.0080 - 0.012 cm/cm	0.0080 - 0.012 in/in	ISO DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	85.0 MPa	12300 psi	ISO 527-93
Elongation at Break	5.5 %	5.5 %	ISO 527-93
Flexural Strength	120 MPa	17400 psi	ISO 178-93
Flexural Modulus	3.95 GPa	573 ksi	ISO 178-93
Izod Impact, Notched (ISO)	8.70 kJ/m ²	4.14 ft-lb/in ²	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	180 °C	356 °F	ISO 75-93
Flammability, UL94	HB @Thickness 0.790 mm	HB @Thickness 0.0311 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China