

Wellman Wellamid® GFT1628-BK 17% Glass Fiber Reinforced, Impact Modified Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 20% Glass Fiber Filled

Material Notes:

Description: Glass Fiber Reinforced, Impact Modified Nylon 66 Information provided by Wellman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellamid-GFT1628-BK-17-Glass-Fiber-Reinforced-Impact-Modified-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.24 g/cc	0.0448 lb/in ³	ISO 1183-87
Filler Content	17 %	17 %	
Linear Mold Shrinkage, Flow	0.0070 - 0.0090 cm/cm	0.0070 - 0.0090 in/in	ISO DIS 294-4
Linear Mold Shrinkage, Transverse	0.0090 - 0.011 cm/cm	0.0090 - 0.011 in/in	ISO DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	105 MPa	15200 psi	ISO 527-93
Elongation at Break	3.0 %	3.0 %	ISO 527-93
Flexural Strength	155 MPa	22500 psi	ISO 178-93
Flexural Modulus	5.10 GPa	740 ksi	ISO 178-93
Izod Impact, Notched (ISO)	10.0 kJ/m ²	4.76 ft-lb/in ²	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	225 °C	437 °F	ISO 75-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China