

Wellman Wellamid® GFX1624-BK(PTFE) 30% Glass Fiber Reinforced, Lubricated Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , 30% Glass Fiber Filled

Material Notes:

Description: Glass Fiber Reinforced, Lubricated Nylon 66 Information provided by Wellman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellamid-GFX1624-BKPTFE-30-Glass-Fiber-Reinforced-Lubricated-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.50 g/cc	0.0542 lb/in ³	ISO 1183-87
Filler Content	30 %	30 %	
Linear Mold Shrinkage, Flow	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	ISO DIS 294-4
Linear Mold Shrinkage, Transverse	0.0080 - 0.010 cm/cm	0.0080 - 0.010 in/in	ISO DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	145 MPa	21000 psi	ISO 527-93
Elongation at Break	2.4 %	2.4 %	ISO 527-93
Flexural Strength	200 MPa	29000 psi	ISO 178-93
Flexural Modulus	9.20 GPa	1330 ksi	ISO 178-93
Izod Impact, Notched (ISO)	8.50 kJ/m ²	4.04 ft-lb/in ²	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	245 °C	473 °F	ISO 75-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China