

## Wellman Wellamid® MR410 22H-NBK1 40% Mineral Reinforced Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , 40% Mineral Filled

**Material Notes:**

Description: Mineral Reinforced Nylon 66 Information provided by Wellman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Wellman-Wellamid-MR410-22H-NBK1-40-Mineral-Reinforced-Nylon-66.php](http://www.lookpolymers.com/polymer_Wellman-Wellamid-MR410-22H-NBK1-40-Mineral-Reinforced-Nylon-66.php)

Physical Properties	Metric	English	Comments
Density	1.49 g/cc	0.0538 lb/in <sup>3</sup>	ISO 1183-87
Filler Content	40 %	40 %	
Linear Mold Shrinkage, Flow	0.0050 - 0.0090 cm/cm	0.0050 - 0.0090 in/in	ISO DIS 294-4
Linear Mold Shrinkage, Transverse	0.010 - 0.014 cm/cm	0.010 - 0.014 in/in	ISO DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	75.0 MPa	10900 psi	ISO 527-93
Elongation at Break	3.0 %	3.0 %	ISO 527-93
Flexural Strength	130 MPa	18900 psi	ISO 178-93
Flexural Modulus	6.835 GPa	991.3 ksi	ISO 178-93
Izod Impact, Notched (ISO)	3.32 kJ/m <sup>2</sup>	1.58 ft-lb/in <sup>2</sup>	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	160 °C	320 °F	ISO 75-93

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China