

Wellman Wellamid® MRGF25/15 42H-BK848 (Interior) 40% Mineral/Glass Fiber Reinforced, 848 Black Color Match Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Glass/Mineral Reinforced

Material Notes:

Description: Mineral/Glass Fiber Reinforced, 848 Black Color Match Nylon 6 Information provided by Wellman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellamid-MRGF2515-42H-BK848-Interior-40-MineralGlass-Fiber-Reinforced-848-Black-Color-Match-Nylon-6.php

Physical Properties	Metric	English	Comments
Density	1.50 g/cc	0.0542 lb/in ³	ISO 1183-87
Filler Content	40 %	40 %	
Linear Mold Shrinkage, Flow	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	ISO DIS 294-4
Linear Mold Shrinkage, Transverse	0.0080 - 0.010 cm/cm	0.0080 - 0.010 in/in	ISO DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	115 MPa	16700 psi	ISO 527-93
Elongation at Break	2.0 %	2.0 %	ISO 527-93
Flexural Strength	160 MPa	23200 psi	ISO 178-93
Flexural Modulus	9.50 GPa	1380 ksi	ISO 178-93
Izod Impact, Notched (ISO)	4.00 kJ/m ²	1.90 ft-lb/in ²	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ISO 75-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China