

Wellman Wellamid® MRT1487 BK Nylon 66, 32% Mineral Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Mineral Filled

Material Notes:

All information provided by Wellman Engineered Resins.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellamid-MRT1487-BK-Nylon-66-32-Mineral-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in ³	ISO 1183-87
Linear Mold Shrinkage, Flow	0.016 - 0.020 cm/cm	0.016 - 0.020 in/in	DIS 294-4
Linear Mold Shrinkage, Transverse	0.014 - 0.018 cm/cm	0.014 - 0.018 in/in	DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	ISO 527-93
Elongation at Break	15 %	15 %	ISO 527-93
Flexural Strength	90.0 MPa	13100 psi	ISO 178-93
Flexural Modulus	3.60 GPa	522 ksi	ISO 178-93
Izod Impact, Notched (ISO)	10.0 kJ/m ²	4.76 ft-lb/in ²	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	70.0 °C	158 °F	ISO 75-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China