

Wellman Wellpet® MRGF101-GY1 PET, 29% Mineral/Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), Glass/Mineral Reinforced

Material Notes:

Typical data obtained from injection molded test bars, tested dry as molded at 73°F (23°C). Information provided by Wellman, Inc. Engineering Resins Division.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellpet-MRGF101-GY1-PET-29-MineralGlass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.54 g/cc	0.0556 lb/in ³	ISO 1183-87
Linear Mold Shrinkage	0.0075 - 0.0095 cm/cm	0.0075 - 0.0095 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.0070 - 0.0090 cm/cm	0.0070 - 0.0090 in/in	DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	95.0 MPa	13800 psi	ISO 527-93
Elongation at Break	2.0 %	2.0 %	ISO 527-93
Flexural Yield Strength	130 MPa	18900 psi	ISO 178-93
Flexural Modulus	8.00 GPa	1160 ksi	ISO 178-93
Izod Impact, Notched	0.590 J/cm	1.11 ft-lb/in	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	250 °C	482 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	205 °C	401 °F	ISO 75-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China