

Westlake EF444 4.7% Ethylene Vinyl Acetate Copolymer (discontinued **)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate

Material Notes:

Excellent haze and gloss, excellent impact strength and very good sealability. Application/Uses High clarity packaging High impact FDA: This material complies with FDA regulations in 21 CFR, section 177.1350. Kosher Compliant. All information provided by Westlake Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_Westlake-EF444-47-Ethylene-Vinyl-Acetate-Copolymer-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.929 g/cc	0.0336 lb/in ³	ASTM D1505
Vinyl Acetate Content	4.7 %	4.7 %	
Thickness	31.8 microns	1.25 mil	
Melt Flow	1.25 g/10 min	1.25 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	300 %	300 %	ASTM D882
Film Elongation at Break, TD	600 %	600 %	ASTM D882
Dart Drop	9.84 g/micron	250 g/mil	ASTM D1709
Film Tensile Strength at Break, MD	27.6 MPa	4000 psi	ASTM D882
Film Tensile Strength at Break, TD	21.4 MPa	3100 psi	ASTM D882
1% Secant Modulus, MD	145 MPa	21000 psi	ASTM D882
1% Secant Modulus, TD	179 MPa	26000 psi	ASTM D882

Optical Properties	Metric	English	Comments
Haze	7.0 %	7.0 %	ASTM D1003
Gloss	63 %	63 %	at 45°; ASTM D2457

Processing Properties	Metric	English	Comments
Melt Temperature	182 - 199 °C	360 - 390 °F	with BUR of 1.5:1 or higher
Blow-up Ratio (BUR)	2.5	2.5	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Process Descriptive Properties	Film Value	Comments
Region	US & Canada	Bamberger Polymers Distribution

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China