

Westlake EN1817AA Low Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE

Material Notes:

Westlake Polyethylene EN1817 is a low density formulation suggested for film applications requiring high clarity, good tear and impact strength, good printability and a wide heat-sealing range. Application/Uses Converter film for food Flexible medical Industrial packaging FDA: This material complies with FDA regulations in 21 CFR, section 177.1520. Kosher Compliant. All information provided by Westlake Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_Westlake-EN1817AA-Low-Density-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in ³	ASTM D1505
Thickness	38.1 microns	1.50 mil	
Melt Flow	1.7 g/10 min @Load 2.16 kg, Temperature 190 °C	1.7 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	300 %	300 %	ASTM D882
Film Elongation at Break, TD	850 %	850 %	ASTM D882
Dart Drop Test	110 g	0.243 lb	ASTM D1709A
Film Tensile Strength at Break, MD	33.8 MPa	4900 psi	ASTM D882
Film Tensile Strength at Break, TD	22.1 MPa	3200 psi	ASTM D882
1% Secant Modulus, MD	207 MPa	30000 psi	ASTM D882
1% Secant Modulus, TD	241 MPa	35000 psi	ASTM D882

Optical Properties	Metric	English	Comments
Haze	6.0 %	6.0 %	ASTM D1003
Gloss	70 %	70 %	at 45°; ASTM D2457

Processing Properties	Metric	English	Comments
Melt Temperature	182 - 193 °C	360 - 380 °F	with BUR of 2.4:1 or higher
Blow-up Ratio (BUR)	2.4	2.4	

Descriptive Properties	Value	Comments
Process	Film	
Region	US & Canada	Bamberger Polymers Distribution

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China