

Westlake Epolene® E-14EP Oxidized Low Molecular Weight Polyethylene Polymer

Category : Polymer , Thermoplastic , Polyethylene (PE)

Material Notes:

Description: The Epolene E-14EP is a low molecular weight, low density, oxidized polyethylene powder. The low molecular weight and low softening point contribute to the production of stable, low color emulsions by both atmospheric (wax-to-water) and pressure emulsification methods. Epolene E-14EP imparts excellent slip resistance to floor polish films. Key Attributes: Imparts slip resistance, durability, and toughness to floor finishes. Low density polyethylene (PE) Oxidized to provide functionality. Produces stable water based emulsions. Application/Uses: Automotive refinish, Automotive Building and Construction, Hot Melt Adhesives, Pressure Sensitive Adhesives, Solventborne Adhesives, Waterborne Adhesives, Wax Modification. Information provided by Westlake Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_Westlake-Epolene-E-14EP-Oxidized-Low-Molecular-Weight-Polyethylene-Polymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.930 - 0.960 g/cc	0.930 - 0.960 g/cc	
Viscosity	150 - 300 cP @Temperature 125 °C	150 - 300 cP @Temperature 257 °F	TXAL-A-XX-G-V-005
Brookfield Viscosity	225 cP @Temperature 125 °C	225 cP @Temperature 257 °F	
Molecular Weight	3600 g/mol	3600 g/mol	

Thermal Properties	Metric	English	Comments
Flash Point	>= 204 °C	>= 399 °F	
Ring & Ball Softening Point	104 °C	219 °F	ASTM E28

Optical Properties	Metric	English	Comments
Gardner Color Number	<= 3.0	<= 3.0	TXAL-A-XX-G-VCC-99

Chemical Properties	Metric	English	Comments
Total Acid Number	17	17	mg KOH/g

Descriptive Properties	Value	Comments
Penetration Hardness	4 dmm	ASTM D5, Needle under 100-g load for 5s @ 25 °C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China