

## Westlake Epolene® N-14P Nonemulsifiable - Low Molecular Weight Polyethylene Polymer

Category : Polymer , Thermoplastic , Polyethylene (PE)

### Material Notes:

Description: Epolene N-14P is a polyethylene (PE) homopolymer powder that can easily be melt blended with natural or synthetic waxes to increase the tensile strength of wax blends, improve the gloss of paper coatings, aid in pigment dispersion and mold release, and improve scuff and rub off resistance in printing inks. For these applications, six Epolene N-types, differing mainly in viscosity, are available to choose from (Epolene N-10, N-11, N-14, N-30, N-34, and N-35). Key Attributes: Aids in pigment dispersion Easy to melt blend with natural or synthetic waxes Improves physical properties of paper coatings Increases scuff and rub off resistance in inks Low density polyethylene (PE)

Application/Uses: Automotive Building and Construction Hot Melt Adhesives Packaging Solventborne Adhesives Wax Modification

Information provided by Westlake Chemical

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Westlake-Epolene-N-14P-Nonemulsifiable-Low-Molecular-Weight-Polyethylene-Polymer.php](http://www.lookpolymers.com/polymer_Westlake-Epolene-N-14P-Nonemulsifiable-Low-Molecular-Weight-Polyethylene-Polymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.910 - 0.950 g/cc	0.910 - 0.950 g/cc	
Viscosity	75 - 200 cP	75 - 200 cP	542-111
Brookfield Viscosity	150 cP @Temperature 125 °C	150 cP @Temperature 257 °F	
Molecular Weight	4000 g/mol	4000 g/mol	

Thermal Properties	Metric	English	Comments
Flash Point	>= 343 °C	>= 649 °F	ASTM E136
Ring & Ball Softening Point	108 °C	226 °F	ASTM E28

Optical Properties	Metric	English	Comments
Gardner Color Number	<= 2.0	<= 2.0	542-130

Descriptive Properties	Value	Comments
Penetration Hardness	3 dmm	ASTM D5, Needle under 100-g load for 5s @ 25 °C

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China