

Westlake Hifor LT74104 Linear Low Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE

Material Notes:

WESTLAKE Hifor Polyethylene LT74104 is a high strength linear low density polyethylene containing no slip or antiblock. It is designed for blown film applications and is well suited for consumer and industrial packaging markets which require good impact and tear strength. Films produced using LT74104 exhibit low imperfections and facilitate production at thinner gauges. Application/Uses Vegetable packaging Bread bags slice bags FDA: This material complies with FDA regulations in 21 CFR, section 177.1520. Kosher Compliant. All information provided by Westlake Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_Westlake-Hifor-LT74104-Linear-Low-Density-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in ³	ASTM D1505
Thickness	25.4 microns	1.00 mil	
Melt Flow	1.0 g/10 min	1.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	750 %	750 %	ASTM D882
Film Elongation at Break, TD	1000 %	1000 %	ASTM D882
Dart Drop	6.69 g/micron	170 g/mil	ASTM D1709
Film Tensile Strength at Break, MD	50.3 MPa	7300 psi	ASTM D882
Film Tensile Strength at Break, TD	39.3 MPa	5700 psi	ASTM D882
1% Secant Modulus, MD	221 MPa	32000 psi	ASTM D882
1% Secant Modulus, TD	241 MPa	35000 psi	ASTM D882

Optical Properties	Metric	English	Comments
Haze	8.0 %	8.0 %	ASTM D1003
Gloss	60 %	60 %	at 45°; ASTM D2457

Processing Properties	Metric	English	Comments
Melt Temperature	204 - 216 °C	400 - 420 °F	
Blow-up Ratio (BUR)	2.4	2.4	

Descriptive Properties	Value	Comments
Process	Film	
Region	US & Canada	Bamberger Polymers Distribution

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China