

Westlake Mxsten CV77523 Polyethylene Plastomer

Category : Polymer , Thermoplastic , Polyethylene (PE)

Material Notes:

Mxsten CV plastomer CV77523 is a polyethylene plastomer designed for blown film extrusion that contains high slip, very high antiblock and polymer processing aid additives. Films produced with this resin exhibit very good strength properties and low seal initiation temperatures. Application/Uses Agricultural tubing Blown film Co-ex films FDA: This material complies with FDA regulations in 21 CFR, section 177.1520. All information provided by Westlake Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_Westlake-Mxsten-CV77523-Polyethylene-Plastomer.php

Physical Properties	Metric	English	Comments
Density	0.906 g/cc	0.0327 lb/in ³	ASTM D1505
Thickness	25.4 microns	1.00 mil	
Melt Flow	0.50 g/10 min	0.50 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, TD	7.58 MPa	1100 psi	ASTM D882
Film Elongation at Break, MD	600 %	600 %	ASTM D882
Film Elongation at Break, TD	1000 %	1000 %	ASTM D882
Elmendorf Tear Strength MD	450 g	450 g	ASTM D1922
Elmendorf Tear Strength TD	650 g	650 g	ASTM D1922
Dart Drop	47.2 g/micron	1200 g/mil	ASTM D1709
Film Tensile Strength at Break, MD	62.1 MPa	9000 psi	ASTM D882
Film Tensile Strength at Break, TD	44.8 MPa	6500 psi	ASTM D882
1% Secant Modulus, MD	124 MPa	18000 psi	ASTM D882
1% Secant Modulus, TD	145 MPa	21000 psi	ASTM D882
Heat Seal Strength Initiation Temperature	82.0 °C	180 °F	Westlake

Optical Properties	Metric	English	Comments
Haze	30 %	30 %	ASTM D1003
Gloss	35 %	35 %	at 45°; ASTM D2457

Processing Properties	Metric	English	Comments
Blow-up Ratio (BUR)	2.4	2.4	

Descriptive Properties	Value	Comments
Process	Blown Film	
	Film	
Region	US & Canada	Bamberger Polymers Distribution

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China